





	IC	D1	L	S
	(mm)	(mm)	(mm)	(mm)
0302	5.556	2.85	3.80	2.38
0402	6.350	3.15	4.30	2.38
0503	7.938	3.20	5.40	3.18
06T3	9.525	3.72	6.50	3.97
0804	12.700	4.30	8.70	4.76



Valores de inicio adecuados para la velocidad de corte (vc), avance (f) y profundidad de corte (ap). Consulte nuestra APP Calculadora de mecanizado para obtener más cálculos.

Producto	RE	P			M			K			N			S			H		
		vc	f	ap	vc	f	ap	vc	f	ap	vc	f	ap	vc	f	ap	vc	f	ap
	(mm)	(m/min)	(mm/rev)	(mm)	(m/min)	(mm/rev)	(mm)	(m/min)	(mm/rev)	(mm)	(m/min)	(mm/rev)	(mm)	(m/min)	(mm/rev)	(mm)	(m/min)	(mm/rev)	(mm)
				Geometría 45 para mecanizado en acabado a desbaste y cortes continuos a interrumpidos.															
WCMX 06T308E-45	D8330 0.8	165	0.15	—	95	0.14	—	155	0.15	—	—	—	—	—	—	—	—	—	—
				Geometría 46 para mecanizado fino a acabado y cortes continuos a interrumpidos.															
WCMX 030208E-46	D8330 0.8	165	0.15	—	95	0.14	—	155	0.15	—	—	—	—	—	—	—	—	—	—
WCMX 040208E-46	D8330 0.8	165	0.15	—	95	0.14	—	155	0.15	—	—	—	—	—	—	—	—	—	—
				Geometría 47 para mecanizado en acabado a semidesbaste y cortes continuos a interrumpidos.															
WCMX 050308E-47	D8330 0.8	165	0.20	—	95	0.18	—	155	0.20	—	—	—	—	—	—	—	—	—	—
				Geometría 48 para mecanizado en acabado a semidesbaste y cortes continuos a interrumpidos.															
WCMX 080412E-48	D8330 1.2	165	0.22	—	95	0.20	—	155	0.22	—	—	—	—	—	—	—	—	—	—